


SPECIFICATIONS

Collection Name	Morse Code 2.0
Construction	Multi-Level Loop
Fiber/Yarn	100% Advance Polypropylene
Colour System	Solution Dyed
Gauge	1/12"
Stitches	10 per inch
Pile Weight	680 g/m²
Average Pile Height	4 mm ± 0.5 mm
Total Height	7 mm ± 0.5 mm
Primary Backing	Non-Woven Premium Fabric
Secondary Backing	E+Bac™ (Fibreglass Reinforced Fine Bitumen)
Tile Size	25cm x 100cm
Installation Method	



Ashlar



Herringbone

PERFORMANCE

Flammability Tests	Test Code	Standard	Test	Results
Radiant Panel	ASTM E 648	Class II	Class II	Pass
Methenamine Pill	ASTM D2859	7 out of 8	8	Pass
Smoke Density	ASTM E 662	Density ≤ 450	≤ 450	Pass
Stability				
Delamination	ASTM D3936	≥3.0 lbs/in		
Dimensional Stability	AACHEN	≤0.2%	≤0.2%	Pass
Tuft Bind	ASTM D1335	≥8.0 lbs	≥8.0 lbs	
Anti-Static				
Static Propensity	AATCC 134	≤3.5 kV	≤3.5 kV	Pass
Colour Fastness				
Light	AATCC 16 E	≥4-5	4-5	Pass
Rubbing/Crocking	AATCC 165	≥4-5	4-5	Pass



NOTE:
All Product Specifications are averages derived from product sample testing and are subject to normal manufacturing tolerances and testing tolerances.

Product Specifications may be changed without notice as long as product performance is not materially affected.

Chair pads are recommended for castor chairs to prevent premature wear of carpets.

Fusion.




SSB



Fusion.

MORSE CODE 2.0

Fusion.



MORSE CODE 2.0

